



Systalen PO-C42001 gr000

PE/PP Compound

Product information

General Data		Form:	pellets		
		Colour:	grey		
		Filtration:	250 µm		
		Source:	flexible post-consumer packaging (content 100 %)		
		PP content:	ca. 30 %		
		Status:	commercial		
Physical Properties		Data	Unit	Test standard	
	Ash content (625 °C):	≤ 4	%	EN ISO 3451-1	
	MFR (190 °C/5 kg):	≈ 5–8	g/10 min	EN ISO 1133	
	MFR (230 °C/2,16 kg):	≈ 3–5	g/10 min	EN ISO 1133	
		Density:	0,96	g/cm ³	EN ISO 1183-1
Mechanical Properties		Data	Unit	Test standard	
	Tensile strength:	17	MPa	EN ISO 527-1/2	
	Tensile modulus:	650	MPa	EN ISO 527-1/2	
	Charpy notched impact strength:			EN ISO 179/1eA	
	23 °C	15	kJ/m ²		
	-20 °C	3,5	kJ/m ²		
Application	Extrusion, injection moulding				
Processing	We recommend to pre-dry the pellets at 70 °C to 80 °C for approx. 2 hours before processing or to add a moisture absorber.				

The material is certified according to EuCertPlast.

The data in this product information are typical properties conforming to our current state of technical know-how and experience and are not to be construed as specification limits. Because of the variety of possible influences during processing and use of our products, they do not exempt the user from his duty to conduct own checks and tests regarding the suitability of the products. The legally binding confirmation of certain properties or of the qualification for a certain purpose cannot be derived. The item is suitable for non-food-products, with the exception for children's toys, medicinal products and cosmetics as defined by the Foods, Consumer Goods and Feedstuffs Code (LFGB). Possible trademark rights as well as existing laws and regulations are to be followed by the user at his own responsibility. We reserve the right to perform modifications.

Systalen – a product manufactured on behalf of:



Der Grüne Punkt – Duales System Deutschland GmbH
 Edmund-Rumpler-Strasse 7, D-51149 Cologne (Gremberghoven)
 Internet: www.gruener-punkt.de | E-mail: info@systalen.de
 Phone: +49(0)2203 / 937-555 | Fax: +49(0)2203 / 937-830

A member company of Der Grüne Punkt Group